



## VF75-N122

This TDS describes a perfluorinated rubber FFKM compound with excellent mechanical and chemical resistance, it has an outstanding resistance at high temperature

This compound is suitable for oils and lubricants sealing in hydraulic and pneumatic application with aggressive media and where extremely high temperature resistance is required compared to standard fluorinated compounds





## VF75-N122

PROPERTY	METHOD	UNITS	VALUE
Color			Black
Specific gravity	ISO 2781	g/cm <sup>3</sup>	1,99
Hardness	ISO 48	IRHD	75
Tensile strength	ISO 37	MPa	19,8
Elongation	ISO 37	%	150
Modulus 100%	ISO 37	MPa	11,8
Tear strength	ISO 34	N/mm	23
Service temperature (min-max)	/	°C	-15/+260
Compression set 72 hrs at 204 °C	ASTM D1414	%	19

### CHEMICAL RESISTANCE GUIDELINE

1 = suitable, little or no effect		3 = Moderate to severe effect – may be useful in some limited applications	
2 = Minor to moderate effect, not maximum resistance		4 = Unsuitable and not recommended – severe effect	
<u>Chemical group</u>	<u>Rating</u>	<u>Chemical group</u>	<u>Rating</u>
Aromatics / Aliphatic oils	1	Esters	1
Acids	1	Ketones	1
Alkalis	1	Propylene Oxide	1
Alcohol's	1	Steam / Hot Water	1
Aldehydes	1	Strong Oxidisers	1
Amines	1		
Ethers	1		
Ethylene Oxide	1		

The data and information contained in this note, while being the result of many years of experience, are only indicative. The company HD Slippers S.r.l. will not be responsible neither for the impact of use of such data, nor for any conflict with existing patents.

**This document is reachable at HD Slippers S.r.l.**