



CR70-N054



This TDS describes a standard Chloroprene rubber compound peroxide cured with good mechanical and chemical resistance

This compound is suitable for sealing in hydraulic and pneumatic specific application





CR70-N054

PROPERTY	METHOD	UNITS	VALUE
Color			Black
Specific gravity	ASTM D297	g/cm ³	1,40±0,03
Hardness	DIN ISO 7619-1	ShA	70±5
Tensile strength	DIN 53 504	MPa	≥14
Elongation	DIN 53 504	%	≥200
Service temperature (min-max)	/	°C	-40/+120
TR10	ASTM D1329	°C	-37
Compression set 24 hrs at 100 °C	DIN ISO 815	%	<20

The data and information contained in this note, while being the result of many years of experience, are only indicative. The company HD Slippers S.r.l. will not be responsible neither for the impact of use of such data, nor for any conflict with existing patents.

This document is reachable at HD Slippers S.r.l.